


# NANOMYTE® NAB-85 (Prussian White)


#### **Material Characteristics**

**Product Description:** Sodium Manganese Hexacyanoferrate ("Prussian White") powder

Formula:  $Na_{1.79}Mn[Fe(CN)_6]_{0.87}$ 

Type: Cathode Structure: Unknown Average Particle Size ( $D_{50}$ ): 1.5  $\mu$ m





Percentiles	
%TileSize(um)	
10.00	0.501
20.00	0.762
30.00	1.002
40.00	1.249
50.00	1.524
60.00	1.839
70.00	2.219
80.00	2.774
90.00	4.05
95.00	5.98

**Issued:** 14-August-2023 (v1.0) Page **1** of **2** 





## NANOMYTE® NAB-85 (Prussian White)

### **Available Quantities**

NANOMYTE® NAB-85 is available in quantities of 25g, 50g, 100g, & 250g. Larger quantities are not available at this time.

### **Precautions for Safe Storage & Handling**

Appropriate personal protective equipment should be used at all times. Avoid contact with eyes and skin, and avoid breathing dust. Provide appropriate exhaust ventilation at places where dust is formed. Keep container tightly closed in a dry and well-ventilated place.

Refer to SDS for complete safety information of this material.

**NOTE:** NEI Corporation believes that the information in this spec sheet is an accurate description of the typical use of the product. However, NEI disclaims any liability for incidental or consequential damages, which may result from the use of their products that are beyond its control. Employers should use this information only as a supplement to other information gathered by them and should make independent judgment of suitability of this information to ensure proper use and protect the health and safety of employees. Therefore, it is the user's responsibility to thoroughly test the product in their particular application to determine its performance, efficacy, and safety. Nothing contained herein is to be considered as permission or a recommendation to infringe any patent or any other intellectual right.

**Issued:** 14-August-2023 (v1.0) Page **2** of **2**