

### Material Characteristics

---

<b>Product Name:</b>	NANOMYTE <sup>®</sup> SP-10C
<b>Product Description:</b>	LATP-coated Lithium Manganese Nickel Oxide (LMNO) powder
<b>Formula:</b>	LiMn <sub>1.5</sub> Ni <sub>0.5</sub> O <sub>4</sub> with 1 – 5 wt% LATP
<b>Phase Purity:</b>	> 98%
<b>Average Particle Size (D<sub>50</sub>):</b>	5 – 8 μm
<b>Specific Surface Area:</b>	1.2 – 1.3 m <sup>2</sup> /g

### Electrical Characteristics

---

<b>Nominal Voltage vs. Li/Li<sup>+</sup>:</b>	4.7V
<b>Minimum Capacity:</b>	110 mAh/g
<b>Nominal Capacity at 0.1C:</b>	≥ 125 mAh/g

### Recommended Operating Conditions

---

<b>Charge Method:</b>	Constant current – constant voltage
<b>Maximum Charge Voltage:</b>	5.0V vs. Li/Li <sup>+</sup>
<b>Maximum Charge Current:</b>	5C
<b>Cutoff Voltage for Discharge:</b>	3.5V vs. Li/Li <sup>+</sup>
<b>Maximum Discharge Current:</b>	5C

### Available Quantities

---

NEI's cathode and anode powders are available for purchase in quantities of 500 grams or more.

### Storage & Handling

---

#### Precautions for Safe Handling

Appropriate personal protective equipment should be used at all times. Provide good ventilation or extraction. Avoid contact with eyes and skin. Wash hands thoroughly after handling.

#### Conditions for Safe Storage

Keep container tightly closed in a moisture-free and well-ventilated place.

**Refer to SDS for complete information on the safe handling of this material.**

**NOTE:** NEI Corporation believes that the information in this spec sheet is an accurate description of the typical use of the product. However, NEI disclaims any liability for incidental or consequential damages, which may result from the use of their products that are beyond its control. Employers should use this information only as a supplement to other information gathered by them and should make independent judgment of suitability of this information to ensure proper use and protect the health and safety of employees. Therefore, it is the user's responsibility to thoroughly test the product in their particular application to determine its performance, efficacy, and safety. Nothing contained herein is to be considered as permission or a recommendation to infringe any patent or any other intellectual right.